



**econfloor**

P O L S K A   S P . Z O . O .

**PRODUCT DATA SHEET**

-EN-

COLLECTION HERRINGBONE 55

## TECHNICAL DATA

### HERRINGBONE 55

| Product                  | SPC Rigid Vinyl floor, Herringbone 55                                            |                          |
|--------------------------|----------------------------------------------------------------------------------|--------------------------|
| Thickness                | 5.7 mm                                                                           |                          |
| Wear layer               | 0.55 mm                                                                          |                          |
| Clicking system          | Pushdown Click-system                                                            |                          |
| IXPE-Aluminium underlay  | 1.7 mm (incl. 0.2 mm aluminium foil)                                             |                          |
| Features                 | Waterproof, Wear-resistant, Anti-slip, Rot-, Fire-, Sound-, Mold-proof           |                          |
| Measurements             | 610 x 126 mm                                                                     |                          |
| Surface treatment        | Ceramic & UV coated, EIR (Embossed in register), Hand-brushed wood               |                          |
| Advantages               | Easy click-system to install, Labor costs saving, Strong stability, Eco-friendly |                          |
| Density                  | 2.0g/cm <sup>3</sup>                                                             |                          |
| Technical data           | Test method                                                                      | Result                   |
| Abrasion resistance      | EN 660-2                                                                         | 42                       |
| Slip resistance          | EN 13893/DIN 51130                                                               | R11 Class                |
| Color fastness           | EN ISO 105-B02                                                                   | ≥6                       |
| Castor chair resistance  | ISO TR4918                                                                       | Passed                   |
| Chemical resistance      | EN ISO 26987                                                                     | Excellent                |
| Flame retardency         | EN 13501-01                                                                      | Bfl-s1                   |
| Toxicity                 | EN 71                                                                            | Non toxic                |
| Dimensional stability    | EN434                                                                            | < 0.06%                  |
| Castor chair effect      | EN425                                                                            | Good                     |
| Underfloor heating       | EN12524                                                                          | Suitable                 |
| Antibacterial properties | EN846                                                                            | Very good                |
| Peel strength            | EN                                                                               | 100N/5cm                 |
| Load test                | EN433                                                                            | 0.03                     |
| Heat resistance          | ---                                                                              | 0.026 m <sup>2</sup> /KW |
| VOC                      | EN 16516                                                                         | A+                       |